



# Technical Data Sheet

4917 Golden Parkway, Suite 300  
Buford, GA 30518  
770-237-2311

Preliminary

Material:  Ecomass® Compound 720ZD88

**Description / Features:** High Specific Gravity, Tungsten Powder Filled ABS, Good Toughness, Plateable  
**Processing Method:** Injection Molding

## Physical Properties

	Test Method	Value	Units
<b>Physical Properties</b>			
Product Form		Pellets	
Specific Gravity	ASTM D792	6.00	g/cc
<b>Mechanical Properties</b>			
Tensile Strength	ASTM D638	2,500	psi
Tensile Modulus			
Tensile Elongation at Break	ASTM D638	1.1	%
Flexural Modulus	ASTM D790	1,250,000	psi
Flexural Strength			
Izod Impact Strength	ASTM D256	1.0	ft-lb/in
<b>Thermal Properties</b>			
Heat Deflection Temperature at 66 psi		Not Available	°F
Heat Deflection Temperature at 264 psi		Not Available	°F
<b>Electrical Properties</b>			
Surface Resistivity		Not Available	ohms/sq
<b>Processing Information</b>			
Melt Temperature Range		400 - 480	°F
Mold Temperature Range		80 - 120	°F
Mold Shrinkage Rate	ASTM D955	0.2	%
Pre-Drying Conditions		2 - 4 Hours @ 160 - 180F	

The information provided above is based on laboratory testing using test methods indicated and is believed to represent nominal results of those tests. Because conditions under which this material may be processed, tested or used cannot be anticipated, no warranty is given, either expressed or implied, as to the accuracy or reproducibility of this information or for the fitness of this material for any particular use. This material is sold with the express understanding that purchasers, processors or other users of this material have sole responsibility, through performance of their own testing, to determine the suitability of this material for any particular use.